

Product information

PLAKAL 70



Major use: Machine made laminating and box covering work. Hand made paper-conversion. Machine made bookcase production. Glue strengthening.

Description: PLAKAL 70 is a protein-based powder-adhesive. It shows a medium open time and good flatlaying properties in 55 % solution. The protein adhesive has no foaming. There is no tendency of spinning during application. PLAKAL 70 is especially suitable for application on laminating machines and boxcovering machines (e.g. Emmeci, Perondi, Crathern, Tünkers, etc.) on account of its quick-tack properties. It is furthermore suitable for the production of bookcase making machines (e.g. Hörauf, Kolbus, Stahl/VBF). Furthermore PLAKAL 70 is used to strengthen other powder- or jelly-glues. In this way even under exceptional conditions good application result are achieved. The protein adhesive remains elastic and free of tension during the drying process. There is no distortion of paper. Plakal 70 is a natural product and colour deviation is normal. The variation in colour has no effect on the quality of the adhesive.

Characteristics:
(55 % solution)

Refractometer value: 52 %

Gelatinising power: instantly, very strong, tacky¹⁾

Gelation point: 38.7 °C²⁾

Open time: medium¹⁾

Instructions for use:

Temperature: 45 - 65 °C

The amount of adhesive per surface unit depends to a high degree on the machine type and the materials to be bonded.

1) This value was determined at 22°C and 40% relative humidity. It is subject to change through changing climatic conditions and changing concentrations of the solution.

2) The gelation or solidification point is defined as the temperature at which the protein adhesive gels (solidifies) under pre-defined conditions.

Preparation directions:**Basic preparation (55 % solution):**

8 parts by volume PLAKAL 70 (550 g)
5 parts by volume water (450 g)

Warm preparation:

Use hot water (70-80°C) and add PLAKAL 70 and stir in a vigorous way; until an homogeneous glue solution is obtained.

Cold preparation:

Use cold water and add PLAKAL 70 whilst stirring; allow the product to swell, preferably overnight. After that, melt the preparation in the glue tank.

The ready for use solution should be consumed within 24 hours.

Storage:

Dry and cool. Material is frost-resistant.

Storage life:

Storage life of at least 1 year if storage conditions are observed.

Delivery specifications:

Appearance: light brown powder

Viscosity: approx. 2700 mPas \pm 600 mPas³⁾
(55 % solution)

Solid content: 100.0 %

Form of delivery:

Powder-adhesive in 25-kg polyethylene-bags (PE).

Disposal:

As a rule PLAKAL 70 is biodegradable or degradable in biological sewage plants. In case of doubt, contact your wastewater management authorities.

Cleaning:

Warm water. We recommend our separating and cleaning agent **PARTINOL**.

For further information please refer to our safety data sheet.

3) Viscosity measure with a Haake rotating viscosimeter at 60°C. As a rule the reading does not coincide with the reading from the viscosimeter on the machine.

The information in the present data sheet is based on current technical knowledge and experience and are without obligation. The aforesaid data and information do not release the worker from his duty of care, in particular his trial and test obligations.

As per 25. May 2010