

Product information

PLAKAL Covertack 520



Major use: Manual lamination and boxcovering work.
Manual paper processing.

Description: PLAKAL Covertack 520 is a protein adhesive with low viscosity. It has a very long open time and is especially suited for manual applications.

Plakal Covertack 520 is a natural product and colour deviation is normal. The variation in colour has no effect on the quality of the adhesive.

Characteristics:
(undiluted adhesive)

Refractometer value: 66 %

Gelatinizing power: instantly, very strong ¹⁾

Gelation point: 30.6 °C ²⁾

Open time: very long

Instructions for use: **Temperature:** 45 - 65 °C

1) This value was determined at 22°C and 40% relative humidity. It is subject to change through changing climatic conditions and changing concentrations of the solution.

2) The gelation or solidification point is defined as the temperature at which the protein adhesive gels (solidifies) under pre-defined conditions.

Preparation directions: PLAKAL Covertack 520 is molten in the heatable circulation tank at 45 - 65 °C. Please avoid temperatures above 70 °C.

When ready for use the solution should be consumed within 24 hours.

Dilution:

Addition of water (%)	0	3	6	9	12	15	18
Refractometer value (%)	65.5	63.5	61.6	59.6	57.6	55.7	53.7

Storage: Dry and cool.

Storage life: Storage life of at least 6 months if storage conditions are observed.

Delivery specifications: Appearance: light brown
Viscosity: approx. 420 mPas ± 50 mPas ³⁾
Solid content: 63.1 %

Form of delivery: Pileable 20 kg cartons containing 8 polythene wrapped portions of 2.5 kg each.

Disposal: As a rule PLAKAL Covertack 520 is biodegradable or degradable in biological sewage plants. In case of doubt, contact your wastewater management authorities.

Cleaning: Warm water. We recommend our separating and cleaning agent **PARTINOL**.

For further information please refer to our safety data sheet.

3) Viscosity measure with a Haake rotating viscosimeter at 60°C. As a rule the reading does not coincide with the reading from the viscosimeter on the machine.

The information in the present data sheet is based on current technical knowledge and experience and are without obligation. The aforesaid data and information do not release the worker from his duty of care, in particular his trial and test obligations.

As per 25. May 2010